

HANOVER® GRANITE PAVERS

Standard & Selected Custom Colors

STANDARD COLOR:	COMPRESSIVE STRENGTH:	DENSITY:	WATER ABSORPTION:	FLEXURAL STRENGTH:
Ashford White	22,713 psi	165 lbs/ft ³	0.33%	2,292 psi
Superior Black	26,800 psi	178 lbs/ft ³	0.14%	2,400 psi
Carnation	28,950 psi	164 lbs/ft ³	0.5%	2,422 psi
Crimson	26,500 psi	167 lbs/ft ³	0.1%	2,300 psi
Evergreen	27,325 psi	177 lbs/ft ³	0.11%	3,452 psi
Mahogany	22,500 psi	167 lbs/ft ³	0.106%	1,598 psi

Stocked Size: 23 1/2" x 23 1/2" x 2" **Stocked Finish:** Thermal/Flamed **Weight:** 2" thickness = 32 lbs/sf **Tolerance:** +/- 1/16"

CUSTOM COLOR:	COMPRESSIVE STRENGTH:	DENSITY:	WATER ABSORPTION:	FLEXURAL STRENGTH:
Blue Pearl	21,030 psi	169 lbs/ft ³	0.04%	1,900 psi
Butterfly Green	18,855 psi	168 lbs/ft ³	0.14%	1,581 psi
Rose Gold	24,746 psi	162 lbs/ft ³	0.32%	1,701 psi
Coral Rose	23,900 psi	167 lbs/ft ³	0.18%	1,545 psi
Golden Yellow	30,864 psi	162 lbs/ft ³	0.43%	2,234 psi
Leopard Skin	16,272 psi	169 lbs/ft ³	0.11%	2,410 psi
Milky Way	21,625 psi	167 lbs/ft ³	0.22%	2,915 psi
Rushmore Gray	26,977 psi	161 lbs/ft ³	0.19%	2,611 psi
Old Red	14,648 psi	164 lbs/ft ³	0.55%	1,973 psi
White Flower	9,645 psi	165 lbs/ft ³	0.19%	2,277 psi

Weight: 2" thickness = 32 lbs/sf **Tolerance:** +/- 1/16"

The colors shown are a sampling of custom colors Hanover® can provide. Available with an approximate 16 week turnaround, color availability varies. Additional custom colors are available when quantities permit. Custom sizes or thicknesses can be accommodated. Colors shown were available at time of printing. Please check with a Hanover® representative to confirm availability.

Please Note: Because granite is a natural product, variations in color and shading will occur. Granite may contain natural fissures which could appear as cracks. What may seem to be a defect, such as inconsistency, mineral concentrations, fissures, veining, and uneven reflections, is inherent to natural stone products and add to its unique aesthetic value.